

# HIGH-STRENGTH FINE-GRAINED WEAR RESISTANT STEEL

**SIDUR 600** is a high-strength fine-grained wear resistant steel. It is intended for use in components that require high resistance to abrasive sliding wear. Typically, the plates made of this steel are used as add-on plates in the areas with extreme wear providing prolonged component lifetime. Material can be welded in the final structures using the GMAW process.

#### STANDARDS

- General technical delivery requirements in accordance with EN 10021.
- Tolerances on dimensions and shape according to EN 10029.
- Delivery requirements for surface condition according to EN 10163-2.
- Ultrasonic testing according to EN 10160.
- Tensile testing at room temperature according to EN ISO 6892-1.
- Impact testing according to EN ISO 148-1.
- Brinell hardness testing according to ISO 6506-1.

# CHEMICAL COMPOSITION

SIDUR 600	С	Si	Mn	Р	S	Cr	Mo	Ni	Ti	В
Max. in %	0.44	1.0	0.8	0.02	0.05	1.3	0.5	2.0	0.04	0.005

The steel contains grain-refining elements.

SIDUR 600	6–25 mm		
CEV* (max. in %)	0.93		

\*CEV = C + 
$$\frac{Mn}{6}$$
 +  $\frac{Cr + Mo + V}{5}$  +  $\frac{Ni + Cu}{15}$ 

#### MECHANICAL PROPERTIES

Thickness	Surface hardness*		
[mm]	HB <sub>10/3000</sub>		
6–25	560–640		

<sup>\*</sup> One measurement per plate.





	Tensile properties*			
Thickness [mm]	R <sub>p0.2</sub> [MPa] min.	R <sub>m</sub> [MPa] min.	A <sub>5.65</sub> [%] min.	
6–25	1500	1700	7	

<sup>\*</sup> For transverse tensile flat test pieces.

	Impact toughness*			
Thickness [mm]	Testing direction	Temperature [°C]	KV <sub>2</sub> [J] min.	
6–25	transverse	-20	20	

<sup>\*</sup> Measured on standard specimen 10 x 10 x 55 mm. The specified minimum value is the average of 3 tests. One individual value may be below the minimum average value specified, provided that it is not less than 70 % of that value. For plate thickness below 12 mm, subsize specimens shall be used. The minimum values of subsize specimens shall be reduced in direct proportion to the cross-sectional area of the test piece.

### DELIVERY CONDITION

• Hot-rolled quarto plates in quenched and tempered condition.

# DIMENSIONS

Thickness [mm]	Width [mm] max.	Length [mm] max.	
6–25	2000	12500	

Plates can only be delivered with trimmed edges.

#### SURFACE CONDITION

- Sandblasted
- Sandblasted and anti-corrosion painted\*
- \* Thickness of the coating is 20–60  $\mu\text{m}.$

# INSPECTION DOCUMENTS

The type of document shall be agreed upon at the time of enquiry and order. A test certificate according to EN 10204/3.1 is issued mandatory.